

J. Environ. Treat. Tech. ISSN: 2309-1185

Journal web link: http://www.jett.dormaj.com https://doi.org/10.47277/JETT/9(1)32



Evalouation of Styrene Acrylo Nitrile (SAN), Butadiene Rubber (BR), Nano-silica (Nano SiO₂) Blend and Nanocomposite in the Presence of Oxoperoxidant Study

Nooredin Goudarzian¹, Soheil Samiei², Fatemeh Safari¹, Seyyed Mojtaba Mousavi³, Seyyed Alireza Hashemi⁴, Sargol Mazraedoost⁵

¹Department of Applied Chemistry, Shiraz Branch, Islamic Azad University, Shiraz, Iran

²Department of Applied Polymer, Shiraz Branch, Islamic Azad University, Darab, Iran

³Department of Chemical Engineering, National Taiwan University of Science and Technology, Taiwan

⁴Department of Mechanical Engineering, Center for Nanofibers and Nanotechnology, National University of Singapore,

⁵Pharmaceutical Sciences Research Center, Shiraz University of Medical Sciences, Shiraz, Iran. 71348-14336

Received: 13/07/2020 Accepted: 20/09/2020 Published: 09/10/2020

Abstract

Polymer-nanosilica composite was prepared using Silica nanoparticles as reinforcing fillers in Styrene Acrylo Nitrile (SAN). Copolymer Styrene Acrylo Nitrile (SAN) is such warm, soft, clear resins that because of having suitable Physical and mechanical properties, have good resistance against chemical also low solvent and cost toward another copolymer styrene that caused to be in a category of much used of them. The effect of increasing nano-silica loadings on the mechanical properties of BR nanocomposites was also studied. Its defect is its fragility that, with its alloying with Butadiene Rubber, prevents its fragility. Basically, with adding inorganic Nano bits, changed strength and modulus of elasticity of plastics while increasing Nano bits decrease the strength of the hit. In this study, copolymer Styrene Acrylo Nitrile considered as a matrix and for increasing mechanical qualities used Nano bits silica diacid. Results of automated tests (XRD), (TGA), (HDT), and (SEM) were a sign of improvement of mechanical and thermal qualities. Nowadays, due to using lots of plastics in various industries, this probability exists that destroyed whit being exposed to direct solar radiation. So light destroyed plastics are very important. In this project whit using Oxoperoxidant blend prepared with the ability of light destruction, so that after one and three months, results show to destroy its lights.

Keyword: Permeability, Oxoperoxidant, Styrene Acrylo Nitrile, Degradation

1 Introduction

In the last decade, polymer nano-composites have drawn significant interest from both industry & academia because they often exhibit remarkable improvements in material properties at a very fine level with very low nanofiller loading when compared to pristine polymer or conventional composites. Polymer nanocomposites are a particular class of polymer composites, a type of reinforced polymer having a two-phase material with the reinforcing phase having at least one dimension in the 10-9 m (nm) scale. It constitutes a new class of material having nano-scale dispersion, typically 1-100 nm, of the filler phase in a given matrix. The outstanding reinforcement of nano-composites is primarily attributed to the large interfacial area per unit volume or weight of the dispersed phase (e.g., 750 m2/g). Silica is an abundant compound over the earth largely employed in industries to produce silica gels, colloidal silica, fumed silica, and so on (1). The nano-sized silica particles are unusual because they are applied in emerging areas like medicine and drug delivery etc. Silica nanoparticles have been used in the industry to reinforce the elastomers as a rheological solute (2-5). Silica nanocomposites have been attracting some scientific interest as well due to the advantage of the low cost of production and in the highperformance features. Studies on nano-silica dispersions in polymer matrices like poly(methyl methacrylate) (6-8), polyethylene (9), and poly (ethylene oxide- 600) (10), were reported. Studies were reported on polymer nanocomposites based on silica and polymers like poly (vinyl alcohol) (11), poly (vinyl pyrrolidone), and chitosan. The mechanical and thermal properties of polymer nanocomposites were found to be enhanced compared to the pristine polymers. Acrylonitrile-Butadiene Rubber (NBR), is a synthetic Rubber, the most widely used rubber in automobiles components such as fuel hoses, gaskets, rollers, and other products in which oil resistance is required along with heat resistance properties (12-14). Rubbers are reinforced with fillers to improve their performance by incorporating materials of conventional fillers such as carbon blacks, silica, clay, talc and calcium carbonate, etc. In recent trends, Rubber Nanocomposites made out of nanofillers were found to exhibit remarkable property enhancements compared to conventional micro composites (15-18). Polymer nanocomposites with layered silicates which

Corresponding author: Seyyed Mojtaba Mousavi, Department of Chemical Engineering, National Taiwan University of Science and Technology, Taiwan. Email: kempo.smm@gmail.com.

are made using typical fillers, (19-21) and carbon nanotubes had attracted significant interest in the improvement of structural properties and the development of new materials having different functional properties (22-25). Sadhu and Bhowmick reported the effect of acrylo-nitrile content on the mechanical, dynamic mechanical and rheological properties of the nano composite. The Role of Organic modifier used with montmorrilite on the formation of nanocomposite in melt compounding process has been studied by Kim and White. Rajkumar et al studied the effect of liquid NBR as dispersion media for dispersing nanographite in NBR matrix and consequently, polymer nano- composites were found to improve its thermal stability (26-31). In the current studies, Styrene Acrylo Nitrile (SAN), Butadiene Rubber (BR), was used as dispersion media to disperse the nanosilica in polymer matrix using conventional mixing techniques. SAN -Nanosilica based Nanocomposites were prepared using BR as dispersion media and conventional mixing processes. The effect of Nanosilica on mechanical and thermal and photo degradation properties of polymer nanocomposites was studied. The dispersion of the silica nano particle in the polymer matrix was studied using scanning electron microscopy [SEM] combined with FTIR. The effect of an increase in nano-silica loadings on the physical properties like tensile strength, modulus and Elongation at break, retention properties after air ageing were studied and momentous changes were found in the properties of SAN/ (BR) polymer nanocomposite (32-37).

2 Materials and Methods

Butadiene Rubber (BR JSR -230), Styrene Acrylo Nitrile (SAN), Nano-silica powder obtained from Nanoshell USA, Styrene acrylonitrile (SAN), (SAN w1540) was supplied by Iran Petro Chemical Co., Ltd. (Iran), [MFR =50 g/10 min (200 g/cm³] Kg), Density = 1.04 Styrene/Butadiene/Styrene (SBS) was supplied by A mole Plastic, Co, Ltd. Iran. Casein is a commercial material; it was brought from local suppliers and used as received, nano-silica used in this study is commercially available as fine amorphous, nonporous and typically spherical particles, white color, specific gravity 1.12, p the size of nano-silica particles was determined by solving them in an ethylene glycol solvent. The size of the nanoparticles is determined to be 61.5 nm. Figure 1 depicts the diagram of the nanoparticle size (PSA) of the nanoparticles.




Figure 1: It depicts the diagram of nanoparticle size (PSA) of the nanoparticles

In the first step, the combination of Styrene Acrylonitrile (SAN) and Butadiene Rubber /nano \sin_2 and using the Oxoperoxidant blend was manually mixed to prepare samples. The materials mentioned above percentages combination mixed in a bag by hand to compare the effect of SAN and BR over the impact and flexibility of the SAN, and because the materials were new and fully packed was delivered from the manufacturing factory, there was no need to dewatering and gas

removing. Adding nano sio₂ and using an Oxoperoxidant blend into SAN, BR combination. To evaluate the biodegradation of composites, Oxoperoxidant mixture, and nano-particles with different amounts were added into the SAN-BR sample, and the samples were prepared. Weight percentages combinations of the prepared samples are presented, as shown in Table 1.

The test specimens, i.e., dumbbell specimens, punched out from the compression molded sheet using Die Cas per ASTM D 412 and utilized for determining physicomechanical properties at the cross-head rate of 500 mm per minute using a universal testing machine (UTM, Zwick 1445). The aging studies were carried out. Evaluate the physical and mechanical properties of all samples with the following conditions, for tensile and impact testing standard for injection (see fig. 2).

3 Results and Discussion

3.1 Mechanical properties test results

3.1.1 Investigating the effect of SAN/BR/nano sio₂/Oxo/on mechanical properties

The mechanical properties of the films depend on intermolecular forces of their polymeric manufacturer chains, the nature of the polymer, fillers, and process conditions. The mechanical properties of pure SAN/BR and SAN/BR/nano sio2/Oxo suspension are shown in. Moreover, in Figures 3 and 5. these results were compared with each other. As can be seen in Figure.5, with the presence of SAN with coupler agent BR, the tensile strength of sample B has increased in comparison with sample A. Generally; SAN/BR are non-polar polymer and polar copolymer respectively. Their mixture in any weight percentage can cause the formation of two-phase morphology. This phenomenon indicates that the SAN/BR are immiscible. However, with an increase in tensile strength, it seems that BR caused an increase incompatibility between two phases and strengthened the joint surface interactions. with an increase in the interface, the stress transfer to the minor stage SAN/BR/nano SiO₂/Oxo occurred more convenient during the process and caused its uniform distribution in the context of a matrix. On the other hand, very high BR adhesion can act as a crosslinking agent. Therefore, by applying external tension, concentrated stress on the BR can cause stress ,loss, and avoid the creation of stress concentration areas on holes and cracks. Also, as can be seen in Figure 5, elongation in sample B has decreased poorly, which is due to the high adhesion force of BR and its strong interaction with SAN. It seems that this strong interaction and surface adhesion did not let the polymer chains move and caused a decrease in elongation. Moreover, as can be seen in Figure 5, the amount of Tensile strength and elongation of samples has decreased in comparison with sample 3% nano sio₂ that is due to the nature of BR that has a less modulus than SAN.




Figure 3: Diagram of the impact index of samples containing different weight percentage nano $\sin_2\%$

Table 1: Formulation for preparation of SAN/BR - Nano-composites

Sample	SAN (%)	BR (%)	N (%)	OXO (%)
SAN/BR	95	5	-	-
SAN/BR(A)	90	10	-	-
SAN/BR(B)	80	20	-	-
SAN/BR(C)	70	30	-	-
SAN/BR(D)	60	40	-	-
SAN/BR 0% N (E)	79	20	1	-
(F) /N 20% SAN/BR	77	20	3	-
SAN/BR/OXO0.5(G)	79.6	19.9	-	0.5
SAN/BR/OXO1(H)	79.2	19.8	-	1
SAN/BR/OXO2(L)	78.4	19.6	-	2




Figure 2: Steps of the manufacturing method, also in step 1, numbers 1-10 shows 1-engine, 2-feeder, 3-cooling jacket, 4-thermocouple, 5-screw

Table 2: Terms of molding, injection, molding blends injection

Samples	Process Temperature (°C)	Mold Temperature (°C)	Pressure injection (Mpa)	Rate Injection $(\frac{mm}{s})$
SAN/BR	180-220	40	25-35	15
/N0 SAN/BR	180-230	50	30-40	15
OXO//N0 SAN/BR	180-220	40	25-35	15




Figure 4: Diagram of the impact index of samples containing different weight percentage BR%




Figure 5: Diagram of the Tensile strength and elongation index of samples containing different weight percentage nano SiO₂




Figure 6: Diagram of the melt flow index of samples containing different weight percentage Nano BR

3.1.2 Thermogravimetric analysis (TGA)

Shimadzu TGA-50 performed TGA test under flowing nitrogen ($20\,ml/min$) Atmosphere by $10\,^{\circ}\text{C}/min$ Temperature growth rate. 6mg of each sample was placed in a platinum pan, and the change in weight vs. temperature was

measured .The above figure shows the results of samples' thermal stability containing various percentage combinations of elastomer polyolefin.




Figure 7: Diagram of the melt flow index of samples containing different weight percentage nano sio₂

By observing the obtained results form (see fig 6 and7) diagram it can be concluded that by rising SAN/BR/nano sio2/Oxo percentage the amount of Hank elastomeric materials in the sample increases and consequently, the fluency decreases and the viscosity also increases thus resulting, melt flow index reduces.




Figure 8: Diagram of Thermal Stability of Blend by TGA

Thermal resistance with 1,3% nanoparticles of weight increase of SAN/BR/nano sio₂/Oxo matrix has increased that was due to the formation of the network in the SAN/BR matrix. With the further increase in the percentage of nano sio₂/Oxo in combination the degradation is shifted to lower temperatures that are due to reduction of percentage combination of SAN/BR in other words, the decreasing in percentage composition of the C-N functional group and In fact, by increasing Acrylonitrile group, alloy's thermal resistance rises. Also, according to the diagram can be seen that thermal degradation of sio₂ nanoparticles and cheese powder starts at about 220°C and thermal resistance of sio₂ nanoparticles, cheese powder, and

OXO are lower that SAN/BR matrix alloy, thus bu increasing their percentages, thermal destruction occurs faster. (See fig 8)

3.1.3 Heat temperature results test (HDT)

The presence of silica nanoparticles in the polymer matrix increases the thermal stability of the polymer nanocomposite..




Figure 9: heat temperature results for samples

3.1.4 X-ray Diffraction (XRD) test results

Figure 10 shows the XRD results of pure sio2 and sample. As can be seen, the related peak to the closite 30B in 2θ is 81.3, which shows that the distance between the layers of sio2 nanoparticle is about 34.18. But this peak in the sample with polymeric context has vanished that is due to foliating of NC layers. As mentioned in the mechanical test sections, presence of OXO as a compatible agent and on the other hand presence of SAN/BR/nano sio2/oxo can led to better dispersion of nano sio2, because OXO polar chains have better compatibility with nano-size particles [61.5nm] and due to applied shear force during the process, it has penetrated the nano sio2 layers and has turned this layers apart. With an increase in distance of silicate layers in nanoparticles, the dispersion quality of nanofillers will increase, and their interaction with the polymeric substrate will be improved. Also, XRD results justified the mechanical properties.




Figure 10: X-Ray Diffraction (XRD) test

3.2 Oxygen permeability tests results

Results of samples oxygen permeability can be seen in Table 3. In Fig. 11 the results of oxygen permeability for samples were compared. As can be seen, with the presence in sample D, the amount of oxygen permeability in comparison with sample E was increased. As mentioned in the steam permeability section, it seems that aggregation nano Sio₂ in the polymer context can lead to the creation of gaps in the polymer context, and thus, gas molecules have the opportunity to pass. The results of the mechanical properties section justified this possibility.





Figure 11: Amount of oxygen permeability for the samples

Table 3: Effects of oxygen permeability

Sample code	Relative humidity (%)	Temperature (°C)	Oxygen permeability (Cm³/m²d bar)
D	24	23	8.63
E	24	23	15.4
F	24	23	14.32
G	24	23	15.86
Н	24	23	7.46



 $Figure \ 12: \ Microscopic \ images \ of \ samples \ containing \ different \ weight \ percentage \ of \ (a,b), \ (c,d), \ (e,f), \ (g,h), \ (k,l)$

Also, the presence of nano SiO₂ in the sample F formulation can lead to an increase in oxygen permeability of this sample in comparison with sample E. On the other hand, the presence of nano sio 2 and oxo in sample G, increasing the oxygen permeability of this sample in comparison with samples. In fact, according to what has been observed, each one of nano sio 2 and Oxo can lead to an increase in oxygen permeability. Also, the simultaneous effect of these two factors can be led to

a significant increase in the amount of oxygen permeability. Also, the same situation has been observed for steam permeability. Also, as mentioned in the steam permeability section and by citing to the XRD and SEM results, these results justified the distribution of fillers between the layers and foliation of nanoparticles. It seems that the placement of the silicate sheets with high surface to volume ratio between the polymer chains has increased the oxygen passage route

distance in the film, and thus these silicate sheets acted as oxygen blockers in the context of a matrix. Also, the highest oxygen blocking is related to the nanocomposite film. Therefore, the order of the oxygen permeability for different samples is as follows.

3.3 Scanning Electron Microscopy (SEM)

Electron microscope was used to capture from the surface of the samples (a,b),(c,d),(e,f),(g,h),(k,l) SAN/BR composite that extracted from soil to investigate surface and microstructure of alloys containing various weight percentages of the samples weight percent of Oxo before degradation, one and three months afterward. The below figures present the waste, and polymer phases rupture due to chain separation increasing in Oxo and Sio2 nano-particles percentages. In general, with the separation of Oxo and Sio2 nano-particles from the polymer matrix, the polymer chains are disjointed. This phenomenon is due to the termination of a link between the materials and the polymer. On one side the interactions of the polar functional groups of whey protein and Sio2 nanoparticles on the other side Non-polar and aliphatic groups is destructed by separation of molecules, and the ruin of these interactions leads to polymer chains rupture, chain length reduction and also, molecular weight that with increasing the percentage of Sio₂ nano-particles and oxo, this reduction has more significant results. The SEM images approved bio degradation of these alloys after one and three months. The rupturing of polymeric phases due to ruptured chains with holes formed in the polymer observed. Finally, composites showed appropriate degradation about mechanical and thermal properties, and flow-ability can be used in full applications such as home appliances and packaging industries (see fig 12).

3.4 scanning electron microscopy (SEM)

The common synthetic polymer that can be attacked includes SAN and BR whit oxo, where tertiary carbon bonds in their chain structures are the centers of attack. Ultraviolet rays interact with these bonds to form free radicals, which then react further with oxygen in the atmosphere, creating carbonyl groups in the main chain. The showing surfaces of products may then discolor and crack, and in extreme cases, complete product disintegration can occur. Oxidation tends to start at tertiary carbon atoms because the free radicals formed here are more stable and longer-lasting, making them more susceptible to attack by oxygen. The carbonyl group can be further oxidized to break the chain, this weakens the material by lowering its molecular weight, and cracks start to grow in the regions affected. Biodegradable SAN/BR can be biologically degraded by photo UV to give low molecular weight molecules. This research aims to understand and find a relationship between photooxidative degradation and yellowing of SAN/BR/nano SiO₂ /oxo copolymer. Furthermore, find a simple method for following the degradation. By changing the microstructure of SAN/BR/nano, sio2 /oxo copolymer UV oxidation can induce photooxidative degradation of the copolymer. The butadiene phase is the main responsible phase that causes the photo-oxidative degradation in SAN/BR/nano SiO₂ /oxo copolymer degradation. Photo-oxidative degradation of SAN/BR/nano sio2/oxo copolymer begins, like all polymers, at the surface, which is directly subjected to UV light. The surface of the SAN/BR/nano sio2 /oxo copolymer, however, shows more damage when compared to the interior part and other polymers. Photo-oxidative degradation of SAN/BR/nano SiO₂/oxo copolymer leads to color development (degradation) on the surface of the UV aged samples. Surface degradation is one of the measures of the extent of photooxidative degradation. This means that as the UV irradiation

time and energy of UV light increase, yellowness at the surface of SAN/BR/nano sio₂/oxo copolymer samples becomes more. *SEM Analysis*. The surface identification and distribution of SAN/BR/nano sio₂/oxo 0.5% and 2% nanocomposites, and 30 and 90 days (day) after the photodegradation was carried out by SEM analysis (see fig 13 to 16).




Figure 13: SEM test of sample 0.5% oxo the 30 days' time (day) after the photodegradation




Figure 14: SEM test of sample 2% oxo the 30 days' time (day) after the photodegradation




Figure 15: SEM test of sample 0.5% oxo the 90 days' time (day) after the photodegradation




Figure 16: SEM test of sample 2% oxo the 90 days' time (day) after the photodegradation

4 Conclusion

In this paper, Preparation of the Oxoperoxidant and mechanical, and oxygen permeability, photodegradation of nanocomposite using the SAN/BR/nano SiO₂/oxo was studied. The results cleared that water adsorption increased in the presence of sio2 nanoparticles. Besides, to study the photodegradation of nanocomposite samples under the soil, XRD and SEM were used. Their results revealed that the existence of the hydroxyl group increased the degradation of the sample. Additionally, adding the Oxoperoxidant to samples had a positive effect on its degradation. The effect of the addition of Nano-silica fillers in SAN/BR Nanocomposites using liquid nano sio2 and oxo dispersion media using conventional mixing techniques was investigated. The addition of Nano-silica increases the thermal resistance of polymer nanocomposites. Improvement in and physical, mechanical properties were found at higher loading of Nanofillers. Also, the simultaneous effect of these two factors can be led to a significant increase in the amount of oxygen permeability. Besides, the same situation has been observed for steam permeability.

Ethical issue

Authors are aware of, and comply with, best practice in publication ethics specifically with regard to authorship (avoidance of guest authorship), dual submission, manipulation of figures, competing interests and compliance with policies on research ethics. Authors adhere to publication requirements that submitted work is original and has not been published elsewhere in any language.

Competing interests

The authors declare that there is no conflict of interest that would prejudice the impartiality of this scientific work.

Authors' contribution

All authors of this study have a complete contribution for data collection, data analyses and manuscript writing.

References

 Barik T, Sahu B, Swain V. Nanosilica—from medicine to pest control. Parasitology research. 2008;103(2):253.

- Chrissafis K, Paraskevopoulos KM, Papageorgiou GZ, Bikiaris DN. Thermal and dynamic mechanical behavior of bionanocomposites: fumed silica nanoparticles dispersed in poly (vinyl pyrrolidone), chitosan, and poly (vinyl alcohol). Journal of applied polymer science. 2008;110(3):1739-49.
- Mousavi SM, Hashemi SA, Ghasemi Y, Amani AM, Babapoor A, Arjmand O. Applications of graphene oxide in case of nanomedicines and nanocarriers for biomolecules: review study. Drug metabolism reviews. 2019;51(1):12-41.
- Mousavi S, Zarei M, Hashemi S. Polydopamine for Biomedical Application and Drug Delivery System. Med Chem(Los Angeles). 2018;8:218-29.
- Amani AM, Hashemi SA, Mousavi SM, Abrishamifar SM, Vojood
 A. Electric field induced alignment of carbon nanotubes: methodology and outcomes. Carbon nanotubes-recent progress: IntechOpen; 2017.
- Sargsyan A, Tonoyan A, Davtyan S, Schick C. The amount of immobilized polymer in PMMA SiO2 nanocomposites determined from calorimetric data. European Polymer Journal. 2007;43(8):3113-27.
- Rittigstein P, Priestley RD, Broadbelt LJ, Torkelson JM. Model polymer nanocomposites provide an understanding of confinement effects in real nanocomposites. Nature materials. 2007;6(4):278-82
- Mousavi SM, Farsi M, Azizi M. Enhancement of rheological and mechanical properties of bitumen using styrene acrylonitrile copolymer. Journal of Applied Polymer Science. 2015;132(17).
- Chrissafis K, Paraskevopoulos K, Pavlidou E, Bikiaris D. Thermal degradation mechanism of HDPE nanocomposites containing fumed silica nanoparticles. Thermochimica Acta. 2009;485(1-2):65-71
- Jia X, Li Y, Cheng Q, Zhang S, Zhang B. Preparation and properties of poly (vinyl alcohol)/silica nanocomposites derived from copolymerization of vinyl silica nanoparticles and vinyl acetate. European Polymer Journal. 2007;43(4):1123-31.
- Lee J, Lee KJ, Jang J. Effect of silica nanofillers on isothermal crystallization of poly (vinyl alcohol): In-situ ATR-FTIR study. Polymer testing. 2008;27(3):360-7.
- Mousavi SM, Hashemi SA, Amani AM, Esmaeili H, Ghasemi Y, Babapoor A, et al. Pb (II) removal from synthetic wastewater using Kombucha Scoby and graphene oxide/Fe3O4. Physical Chemistry Research. 2018;6(4):759-71.
- Mousavi S, Aghili A, Hashemi S, Goudarzian N, Bakhoda Z, Baseri S. Improved morphology and properties of nanocomposites, linear low density polyethylene, ethylene-co-vinyl acetate and nano clay particles by electron beam. Polymers from Renewable Resources. 2016;7(4):135-53.
- 14. Mousavi M, Hashemi A, Arjmand O, Amani AM, Babapoor A, Fateh MA, et al. Erythrosine adsorption from aqueous solution via decorated graphene oxide with magnetic iron oxide nano particles: kinetic and equilibrium studies. Acta Chimica Slovenica. 2018;65(4):882-94.
- Vollath D, Szabó DV. Synthesis and properties of nanocomposites. Advanced Engineering Materials. 2004;6(3):117-27.
- Mousavi S, Esmaeili H, Arjmand O, Karimi S, Hashemi S. Biodegradation study of nanocomposites of phenol novolac epoxy/unsaturated polyester resin/egg shell nanoparticles using natural polymers. Journal of Materials. 2015;2015.
- Bahrani S, Hashemi SA, Mousavi SM, Azhdari R. Zinc-based metal-organic frameworks as nontoxic and biodegradable platforms for biomedical applications: review study. Drug metabolism reviews. 2019;51(3):356-77.
- Hashemi SA, Mousavi SM, Arjmand M, Yan N, Sundararaj U. Electrified single-walled carbon nanotube/epoxy nanocomposite via vacuum shock technique: Effect of alignment on electrical conductivity and electromagnetic interference shielding. Polymer Composites. 2018;39(S2):E1139-E48.
- Wu Y-P, Wang Y-Q, Zhang H-F, Wang Y-Z, Yu D-S, Zhang L-Q, et al. Rubber-pristine clay nanocomposites prepared by cocoagulating rubber latex and clay aqueous suspension. Composites Science and Technology. 2005;65(7-8):1195-202.
- Hashemi SA, Mousavi SM, Faghihi R, Arjmand M, Sina S, Amani AM. Lead oxide-decorated graphene oxide/epoxy composite towards X-Ray radiation shielding. Radiation Physics and Chemistry. 2018;146:77-85.

- Hashemi SA, Mousavi SM. Effect of bubble based degradation on the physical properties of Single Wall Carbon Nanotube/Epoxy Resin composite and new approach in bubbles reduction. Composites Part A: Applied Science and Manufacturing. 2016;90:457-69.
- Ajayan PM, Zhou OZ. Applications of carbon nanotubes. Carbon nanotubes: Springer; 2001. p. 391-425.
- Coleman JN, Khan U, Gunko YK. Mechanical reinforcement of polymers using carbon nanotubes. Advanced materials. 2006;18(6):689-706.
- Mousavi SM, Hashemi SA, Arjmand M, Amani AM, Sharif F, Jahandideh S. Octadecyl amine functionalized Graphene oxide towards hydrophobic chemical resistant epoxy Nanocomposites. ChemistrySelect. 2018;3(25):7200-7.
- Mousavi SM, Goudarzian N, Hashemi S. Unsaturated polyester resins modified with cresol novolac epoxy and silica nanoparticles: processing and mechanical properties. International Journal of Chemical and Petroleum Sciences. 2016;5(1):13-26.
- 26. Sadhu S, Bhowmick AK. Preparation and properties of nanocomposites based on acrylonitrile—butadiene rubber, styrene butadiene rubber, and polybutadiene rubber. Journal of Polymer Science Part B: Polymer Physics. 2004;42(9):1573-85.
- Sadhu S, Bhowmick AK. Unique rheological behavior of rubber based nanocomposites. Journal of Polymer Science Part B: Polymer Physics. 2005;43(14):1854-64.
- 28. Mousavi SM, Hashemi SA, Amani AM, Saed H, Jahandideh S, Mojoudi F. Polyethylene terephthalate/acryl butadiene styrene copolymer incorporated with oak shell, potassium sorbate and egg shell nanoparticles for food packaging applications: control of bacteria growth, physical and mechanical properties. Polymers from Renewable Resources. 2017;8(4):177-96.
- Hashemi SA, Mousavi SM, Ramakrishna S. Effective removal of mercury, arsenic and lead from aqueous media using Polyaniline-Fe3O4-silver diethyldithiocarbamate nanostructures. Journal of Cleaner Production. 2019;239:118023.
- Mousavi SM, Hashemi SA, Babapoor A, Medi B. Enhancement of Rheological and Mechanical Properties of Bitumen by Polythiophene Doped with Nano Fe 3 O 4. JOM. 2019;71(2):531-40
- Mousavi S, Arjmand O, Talaghat M, Azizi M, Shooli H. Modifying the properties of polypropylene-wood composite by natural polymers and eggshell Nano-particles. Polymers from Renewable Resources. 2015;6(4):157-73.
- Mousavi S, Arjmand O, Hashemi S, Banaei N. Modification of the epoxy resin mechanical and thermal properties with silicon acrylate and montmorillonite nanoparticles. Polymers from Renewable Resources. 2016;7(3):101-13.
- Mousavi SM, Hashemi SA, Ghasemi Y, Atapour A, Amani AM, Savar Dashtaki A, et al. Green synthesis of silver nanoparticles toward bio and medical applications: review study. Artificial cells, nanomedicine, and biotechnology. 2018;46(sup3):S855-S72.
- Mousavi S, Hashemi S, Zarei M, Amani A, Babapoor A. Nanosensors for Chemical and Biological and Medical Applications. Med Chem (Los Angeles). 2018;8(8):2161-0444.1000515.
- BARIKBIN B, MAAREFAT A, RAHGOSHAI R, MORAVVEJ H, MOHTASHAM N, YOUSEFI M. Malva sylvestris in the treatment of hand eczema. 2010.
- Mousavi SM, Hashemi SA, Zarei M, Bahrani S, Savardashtaki A, Esmaeili H, et al. Data on cytotoxic and antibacterial activity of synthesized Fe3O4 nanoparticles using Malva sylvestris. Data in brief. 2020;28:104929.
- 37. Tech JET. Investigating the Activity of Antioxidants Activities Content in Apiaceae and to Study Antimicrobial and Insecticidal Activity of Antioxidant by using SPME Fiber Assembly Carboxen/Polydimethylsiloxane (CAR/PDMS). Journal of Environmental Treatment Techniques. 2020;8(1):214-24.